

Product information | TECHNICAL DATA SHEET

TWO-COMPONENT EPOXY PRIMER

400 ml.

GENERAL DESCRIPTION

Two-component primer with great anti-corrosion properties. Designed for professional, industrial and automotive purposes, for both indoor and outdoor.

FEATURES

- Easy to apply and repaint.
- High-filling power.
- Multisurface adhesion.
- Very good corrosion resistance.
- Can be recoated with most 1K and 2K paints.

INSTRUCTIONS FOR USE

- Remove the white button from the lid. Turn the can upside down and place the button on the stem on the bottom side of the aerosol.
- Place the aerosol on a firm ground and press the white button with the palm of your hand.
- After activation, shake the aerosol for 2 minutes to ensure a good mixing of the product and catalyst.
- Remove the spray lock by first removing the spray nozzle. Place a screwdriver between the strap and lock ring. Lever the safety catch gently upwards and out.
- Apply on clean, sanded and dry surfaces.
- Apply in thin layers for best results. Recoat with the same product WEPRO Epoxy Primer after 10-15 minutes.
- Can be finished with most 1K and 2K paints.
- Can be topcoated after 6-8 hours and within 72 hours.
- If willing to topcoat after 72 hours, it must be sanded and cleaned beforehand.
- Ready.
- Do not apply 2K putties within first 24 hours.
- Wet sanding with P800 / Dry sanding with P400-P500.
- Pot life: 48 hours.
- Turn the aerosol upside down to clean out the valve after use. If the nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas. Do not breathe the aerosol vapors.
- Use personal protective equipment such as glasses, mask and gloves.
- Request safety datasheets.

* The information provided in this technical data sheet is based on our current knowledge and is intended as a guide for proper application. We do not guarantee specific results and accept no responsibility for the accuracy, completeness, or proper use of the product.

PHYSICAL PROPERTIES

Binding type:	Epoxy
Hardener:	Amine
Color:	White
Dry to the touch (ASTM D-1640 ISO 1517):	3-5 h
Total drying (ASTM D-1640 ISO 1517):	72 h
Coat thickness (ASTM D-823 ISO 2808):	20 microns/layer
Ready for sanding:	24-48h
Theoretical yield (continuous painting):	0,75 m ²
*Potlife:	48 h
Shelf life:	(Well Stored) 3 Years
Application conditions:	T° environment min. 8°C
	T° surface min. 5-50°C
	Humidity Max. 50% R.H.P

* Adherence tests were performed on steel.

070225

APPLICATIONS

Ideal for professional and industrial projects on a variety of surfaces: wood, metal, cast iron, galvanized steel, stainless steel, aluminium, and many plastics (hard PVC, ABS, etc.). On difficult surfaces, carry out a test application.

Specially designed for automotive, industrial and professional use: indoor and outdoor metal furniture, vehicle parts, gutters, gates, railings, fences, garage doors, bicycles, metallic structures, aluminum profiles, industrial and agricultural machinery, urban furniture, etc.

IMAGE



LABEL



Blanco / White
EX014PK0005

CAP SYSTEM



Pocket Cap
Fino - Fine

PACKAGING

Nominal capacity 400 ml.
Heat resistance of packaging: <50°C
Propellant: DME

Box (6 units)
216 X 147 X 220 mm.



Certified ENTERPRISE according to quality and environmental standards
ISO 9001 - ISO 14001

Made in Europe.